# Marrutt 250gsm Smooth Lustre Double Sided

marrutt.com/lustreds

## Paper Description

An ultra white RC inkjet paper coated on both sides with a smooth subtle gloss surface.
The advanced coating with its pleasant sheen provides pin sharp detail, high colour consistency and gamut with an outstanding lay-flat performance - perfect for photobooks and albums.
Used by numerous high-end professional photographers and designers worldwide.

## Paper Specification

| | | | |
|---|---|---|---|
| Weight (gsm) | 250gsm | OBA Content: | Yes |
| Thickness (microns / inches) | 245 / 0.016 | Base Material: | Resin Coated |
| Whiteness (CIE) | > 143 | Surface Finish: | Minimal Texture Gloss |
| Opacity min. ISO 2469 | % > 95 | Coating Type: | Microporous Gloss |
| pH | 7.5-9.5 | | |

## Paper Options / Printer Settings

| | |
|---|---|
| Sheet Sizes: | A4, A3, 6x4, 7x5, 10x8, A5 & A6. Others on request |
| Roll Sizes: | N/A |
| Epson Printer Settings: | Epson Premium Lustre - Photo Black Ink |
| Canon Printer Settings: | Photo Paper Plus Semii Gloss / Photo Paper Pro Lustre |
| Hewlett-Packard (HP) Printer Settings: | HP Premium Plus Semi-gloss Photo Paper |
| Compatible with these inkjet printers: | Epson, Canon, HP and other Inkjet Printers |
| Ink Type: | Pigment and Dye |

### Paper Handling:
Unless the paper is loaded in the printer about to be used, your paper should ALWAYS be kept in its box with the lid on.
In use, avoid touching coated surface before & after printing and wear cotton gloves if necessary.

### Storage advice:
The paper should be kept indoors in a dry environment away from extreme temperatures. The recommended storage temperatures are 15° to 25° C (60° to 77° F) and / or in the dark, with humidity being low, from 40 to 60 percent.
Prints should be allowed to dry in air, ideally left uncovered for 24 hours. In cases where stacking in unavoidable, a paper / tissue interleaf should be placed between each sheet.